

(予熱 : 約300℃)

母材		硬度測定値			平均硬さ
		1	2	3	
SKH-51(予熱)		844	802	803	816
	母材硬度				
	レーザー照射部				

溶接線材	肉盛厚さ	硬度測定値			平均硬度
		1	2	3	
三和/SKH-51					
φ0.2	1層				
	2層				
	3層				
φ0.3	1層	808	838	815	820
	2層	797	791	794	794
	3層	816	776	799	797
φ0.4	1層				
	2層				
	3層				

溶接線材	肉盛厚さ	硬度測定値			平均硬度
		1	2	3	
ステイヒル/GS60					
φ0.25	1層				
	2層				
	3層				
φ0.3	1層	507	578	494	526
	2層	560	477	494	510
	3層	495	497	467	486
φ0.4	1層				
	2層				
	3層				

